



# RHINO

## Cement Quick Curing /Waterproofing Agent QW90

### 英泥快乾防水劑

#### Description

\*QW90 is being used as rapid curing agent for cement mortar, if early strength and time saving is required.

\*Waterproofing property makes it ideal for basement, subway and bathroom; etc.

#### Important

\*QW90 must be combined with fresh cement.

\*The mixed cement mortar must be finished before initial setting.

\*It should NOT be used for structural column purpose.

#### Caution

\*Keep out of reach of children.

\*Storage: Store in unopened original container, kept under cool and safe place.

\*Disposal: Do not allow to be disposed into sewage, soil or water drain.

#### 說明

\*用作英泥快乾劑用,加速英泥凝固,可按須要加入 QW 90 以控制施工時間.

\*其防水效能適用於地庫,隧道及浴室之英泥沙漿批盪工程.

#### 注意

\*必須使用新鮮英泥

\*已混和 QW 90 之英泥須於初凝前用完.

\*QW 90 不可用於作為結構性樑柱之英泥.

#### 小心

\*避免兒童接觸

\*儲存於原裝密封罐內,放於陰涼安全地方.

\*必須棄置於安全棄置區

# Cement Quick Curing /Waterproofing Agent QW90 P.2

## Quick curing 英泥快乾用

(Drying Time 凝固時間)

QW90	Water 水	英泥 Cement: Sand 沙	
		100%: 100%	33%: 67%
100%	0%	minutes 分鐘	2 minutes 分鐘 3
50%	50%		15 25
33%	67%		40 60
25%	75%		70 100
20%	80%		120 150

(25°C 75% RH

By weight 重量計)

## Waterproofing 防水用

Pre-mixed Mixture = 1 Kg QW90 + 14 Kg Water

預調混合劑 = 1 Kg QW90 + 14 Kg 水

Material mixing ratio 材料混合比例：

Mortar Thickness 沙漿厚度	Pre-mixed Mixture 預調混合劑	Cement 英泥	Sand 沙
10 mm	3 Kg	6 Kg	12 Kg
15mm	4.5 Kg	9 Kg	18 Kg
30 mm	9 Kg	18 Kg	36 Kg

**FULITEK CHEMICAL CO., LTD.**