

TAJNA SHELLAC

Machine made Shellac - colour: orange

TECHNICAL DATA FOR SHELLAC

ACID VALUE	65 – 70 mg KOH/g
SAPONIFICATION VALUE	200 – 220 mg KOH/g
MELTING TEMPERATURE	77 – 83 dig. C
MOISTURE	Approx. 1% - 2 %
WAX CONTENT	About 5.5%
ASH	Max. 0.3%
LEAD CONTENT	< 2 ppm
ROSIN	N I L
IMPURITIES IN HOT ALCOHOL	1 - 1½% Max